AFEC E.R.M.A Ltd.

P.O.B 13379 Industrial Zone Nenanya, 4237927, Israel

Tel. +972-72-2121311 Fax. +972-72-2121811 E-mail: info@afecerma.com



אפק א.ר.מ.ע בע״מ

ת.ד 13379 אזוה"ת הישן, נתניה 4237927 טל. 272121311 072-2721 פקס. 272121811 072-2121811 דוא"ל. info@afecerma.com

www.afec-erma.com

Product name: M-110

Supplier: AFEC e.r.m.a Ltd.

Manufacturer: AFEC e.r.m.a Ltd.

Description: M-110 is a powdered admixture for white mortar that is

supplied to construction sites in mobile mixers or in big bags. It is specially formulated for use as an air entraining agent for mortar of all types and is manufactured under rigid control which assures uniform and precise performance.

Fields of Applications: Admixture for manufacturing inside and outside walls

plaster and preparing a base layer for plaster.

Advantages: M-110 gives the white mortar workability and flexibility

which makes it easier to pump, and does not allow the water to evaporate. By lowering the water tension **M-110** helps

plastering work to become easier.

M-110 enables the mortar mix a "regeneration" property

even after few weeks.

M-110 reduces the "blooming" effect of plaster.

Directions of use: M-110 has to be put in the mixer before the first amount of

water. The admixture should be mixed for 5-7 minutes in the fastest range possible. After the addition of quarry and natural sand the water amount must be adjusted. The final air quantity in the mortar mixture depends on the quantity of **M-110**, the fines grading, time and speed of the mixer.

Precautions and Overdose of **M-110** will content a lot of air and reduce the

Limitations: strength of the mortar.

Do not apply **M-110** to a ready mortar mix.

Remarks: Before beginning the work, you should water the wall for at

least 10 minutes, let it dry and then start plastering.

Accumulation: Powder

Chemical Stability: Stable between 6°c-55°c

AFEC E.R.M.A Ltd.

P.O.B 13379 Industrial Zone Nenanya, 4237927, Israel

Tel. +972-72-2121311 Fax. +972-72-2121811 E-mail: info@afecerma.com





ת.ד 13379 אזוה"ת הישן, נתניה 13379 טל. 1237927 טל. 212121311-072 פקס. 272121811 072-217811 דוא"ל. info@afecerma.com

Possible Health Low toxic range.

Influence: Do not swallow.

May irritate eyes.

First Aid: Rinse with water and seek medical advice.

Personal Hygiene: Do not inhale! Protect eyes during use. Use relevant shield.

Rinse hands after use.

Dosage: 1 portion for 1m³ white mortar

Package: Inner lamination paper bags containing 2-9 portions

Handling & storing: Closed packages in dry room—up to six months