

AFEC E.R.M.A Ltd.

P.O.B 13379 Industrial Zone Nenanya, 4237927, Israel
Tel. +972-72-2121311
Fax. +972-72-2121811
E-mail: info@afecerma.com



www.afec-erma.com

אפק א.ר.מ.ע בע"מ

ת.ד. 13379 אזורת הישן, נתניה 4237927
טל. 072-2121311
פקס 072-2121811
אימייל info@afecerma.com

Product name:	M-116
Supplier:	AFEC e.r.m.a Ltd.
Manufacturer:	AFEC e.r.m.a Ltd.
Description:	M-116 is an admixture for white mortar that is supplied to construction sites in mobile mixers or in big bags. It is specially formulated for use as an air entraining agent for mortar of all types and is manufactured under rigid control which assures uniform and precise performance.
Fields of applications:	Admixture for manufacturing inside and outside walls plaster and preparing a base layer for plaster.
Advantages:	M-116 gives the white mortar workability and flexibility which makes it easier to pump, and does not allow the water to evaporate. By lowering the water tension M-116 helps plastering work to become easier. M-116 enables the mortar mix a "regeneration" property even after few weeks. M-116 reduces the "blooming" effect of plaster.
Direction for use:	M-116 has to be put in the mixer with the first amount of water before the quarry and natural sand. The mixture should be mixed for 5 minutes in the fastest range possible. The final air quantity in the mortar mixture depends on the quantity of M-116, the fines grading, time and speed of the mixer.
Precautions and limitations:	Overdose of M-116 will content a lot of air and reduce the strength of the mortar.
Remarks:	Before beginning the work, you should water the wall for at least 10 minutes, let it dry and then start plastering.

AFEC E.R.M.A Ltd.

26 Hadar st. Matan 45858, Israel

Tel. +972-72-2121311

Fax. +972-72-2121811

E-mail: info@afecerma.com



www.afec-erma.com

אפק א.ר.מ.ע בע"מ

רח' הדר 26, מתן 45858

טל. 072-2121311

פקס. 072-2121811

דוא"ל. info@afecerma.com

Accumulation:	Liquid
Chemical Stability:	Stable between 6°C-55°C
Possible health Influence:	Low toxic range. Do not swallow.
First aid	Rinse with water and seek medical advice.
Personal Hygiene:	Do not inhale! Protect eyes during use. Use relevant shield. Rinse hands after use.
Dosage:	1 portion (0.33 liter) for 1m ³ white mortar
Package:	Plastic container volume 2 (6 portions) / 1000 liter
Handling & storing:	Closed packages – up to six months in closed containers